


Prüfbericht - Nr.: 0114040833b 001 <i>Test Report No.:</i>		Seite 1 von 4 <i>Page 1 of 4</i>													
Auftraggeber: <i>Client:</i>		LIEN SHENG PLASTIC INDUSTRY CO., LTD No.111, Ln. 840, Sec. 1, Zhongzheng E. Rd., Dayuan Dist., Taoyuan City 33745, Taiwan, R.O.C.													
Gegenstand der Prüfung: BB pellet <i>Test Item:</i>															
Bezeichnung: <i>Identification:</i>		PLA 0.28g													
Anlieferungszustand: <i>Delivery condition:</i>		apparent good													
		Eingangsdatum: <i>Date of Receipt:</i>													
		2015-09-18													
Prüfort: <i>Testing location:</i>		Laboratories of TÜV Rheinland Taiwan													
Prüfgrundlage: <i>Test specification:</i>		Testing according to customers specification for the following parameter: Material analysis													
Prüfergebnis: <i>Test result:</i>		The test results are the measurements, stated in the test report.													
geprüft: tested by:  2015-10-07 Sunny Hu /Senior Specialist kontrolliert: checked by:  2015-10-07 Tammy Wang /Project Manager <table border="1" style="width: 45%; border-collapse: collapse;"> <tr> <th style="text-align: left;">Datum</th> <th style="text-align: left;">Name/Stellung</th> <th style="text-align: left;">Unterschrift</th> </tr> <tr> <td style="text-align: left;">Date</td> <td style="text-align: left;">Name/Position</td> <td style="text-align: left;">Signature</td> </tr> </table> <table border="1" style="width: 45%; border-collapse: collapse;"> <tr> <th style="text-align: left;">Datum</th> <th style="text-align: left;">Name/Stellung</th> <th style="text-align: left;">Unterschrift</th> </tr> <tr> <td style="text-align: left;">Date</td> <td style="text-align: left;">Name/Position</td> <td style="text-align: left;">Signature</td> </tr> </table>				Datum	Name/Stellung	Unterschrift	Date	Name/Position	Signature	Datum	Name/Stellung	Unterschrift	Date	Name/Position	Signature
Datum	Name/Stellung	Unterschrift													
Date	Name/Position	Signature													
Datum	Name/Stellung	Unterschrift													
Date	Name/Position	Signature													
Sonstiges/ Other Aspects: Test period: 2015-09-18 – 2015-10-07															
Abkürzungen: ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar Abbreviations: ok / P = passed fail / F = failed n.a. / N = not applicable															
Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens. <i>This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.</i>															



Test Report No. : 0114040833b 001
Customer : LIEN SHENG PLASTIC INDUSTRY CO., LTD

2015-10-07

Sample list:

Mat. No.	Lab no.	Product Name	Material	Color
1	TCL150918-09	PLA 0.28g	Plastic	White

Test sample



Remark:

1. Material Analysis
 - 1.1 Infrared rays analysis see attached spectrogram 1
 - 1.2 Differential Scanning Calorimeter see attached graph 2
 - 1.3 Thermogravimetric Analysis see attached graph 3
 - 1.4 Wavelength: $4000\text{ cm}^{-1} \sim 600\text{ cm}^{-1}$
2. Volatile Solids Content
 - 2.1 Sample Weight: 5.5351 g


Test Report No. : 0114040833b 001
Customer : LIEN SHENG PLASTIC INDUSTRY CO., LTD

2015-10-07

Sample/Material No.	1
Material Analysis SOP-C025-01*	The main material of the sample is determinate as PLA (Polylactic acid), with FTIR (Fourier transform infrared spectroscopy) and DSC (Differential Scanning Calorimeter) analysis. + 17.7 % BaSO ₄ Inorganic Filler Content: 20.9 % CaCO ₃ + 57.2 % BaSO ₄
Volatile Solids Content EN 13432	21.6 %

*the method has been certified by ISO/IEC 17025


Attached spectrogram 1




Test Report No. : 0114040833b 001
Customer : LIEN SHENG PLASTIC INDUSTRY CO., LTD

2015-10-07

Attached graph 2



Attached graph 3



--- End of Test-Report ---