





Prüfbericht - Nr.: 0114054256b 002 <i>Test Report No.:</i>		Seite 1 von 4 <i>Page 1 of 4</i>					
Auftraggeber: <i>Client:</i>		LIEN SHENG PLASTIC INDUSTRY CO., LTD No.111, Ln. 840, Sec. 1, Zhongzheng E. Rd., Dayuan Dist., Taoyuan City 33745, Taiwan, R.O.C.					
Gegenstand der Prüfung: BB Pellet <i>Test Item:</i>							
Bezeichnung: <i>Identification:</i>		PLA 0.45g					
Anlieferungszustand: <i>Delivery condition:</i>		Eingangsdatum: <i>Date of Receipt:</i>					
apparent good		2016-08-03					
Prüfort: <i>Testing location:</i>							
Laboratories of TÜV Rheinland Taiwan							
Prüfgrundlage: <i>Test specification:</i>							
Testing according to customers specification for the following parameter: Material analysis							
Prüfergebnis: <i>Test result:</i>							
The test results are the measurements, stated in the test report.							
geprüft: tested by:		kontrolliert: checked by:					
							
2016-10-27 Sunny Hu /Senior Specialist		2016-10-27 Tammy Wang /Project Manager					
Datum <i>Date</i>	Name/Stellung <i>Name/Position</i>	Unterschrift <i>Signature</i>	Datum <i>Date</i>				
2016-10-27	Sunny Hu /Senior Specialist		2016-10-27				
2016-10-27	Tammy Wang /Project Manager		2016-10-27				
Sonstiges/ Other Aspects: Test period: 2016-08-12 – 2016-10-20 This test report supersedes test report no. 0114054256b 001.							
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; vertical-align: top;"> Abkürzungen: </td> <td style="width: 50%; vertical-align: top;"> Abbreviations: </td> </tr> <tr> <td> ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar </td> <td> ok / P = passed fail / F = failed n.a. / N = not applicable </td> </tr> </table>				Abkürzungen:	Abbreviations:	ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar	ok / P = passed fail / F = failed n.a. / N = not applicable
Abkürzungen:	Abbreviations:						
ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar	ok / P = passed fail / F = failed n.a. / N = not applicable						
Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens. <i>This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.</i>							



Test Report No. : 0114054256b 002
Customer : LIEN SHENG PLASTIC INDUSTRY CO., LTD

2016-10-27

Sample list:

Mat. No.	Lab no.	Product Name	Material	Color
1	TCL160803-12B	PLA 0.45g	Plastic	White

Test sample



Remark:

1. Material Analysis
 - 1.1 Infrared rays analysis see attached spectrogram 1
 - 1.2 Differential Scanning Calorimeter see attached graph 2
 - 1.3 Thermogravimetric Analysis see attached graph 3
 - 1.4 Wavelength: $4000\text{ cm}^{-1} \sim 600\text{ cm}^{-1}$
2. Volatile Solids Content
 - 2.1 Sample Weight: 2.2413 g


Test Report No. : 0114054256b 002
Customer : LIEN SHENG PLASTIC INDUSTRY CO., LTD

2016-10-27

Sample/Material No.	1
Material Analysis SOP-C025-01*	The main material of the sample is determinate as Polylactic acid (PLA), with FTIR (Fourier transform infrared spectroscopy) and DSC (Differential Scanning Calorimeter) analysis. Inorganic Filler Content: 85.1 % BaSO ₄ + Cerium Oxide
Volatile Solids Content EN 13432	14.30 %

*the method has been certified by ISO/IEC 17025


Attached spectrogram 1




Test Report No. : 0114054256b 002
Customer : LIEN SHENG PLASTIC INDUSTRY CO., LTD

2016-10-27

Attached graph 2



Attached graph 3



--- End of Test-Report ---